

## 17-4PH - UNS S17400 – H1150D

### MATERIAL DESCRIPTION

UNS S17400 is a grade of martensitic precipitation hardened stainless steel. The name comes from the chemical makeup which is approximately 17% chromium and 4% nickel. 17-4 can be heat treated to high levels of strength and hardness, and features corrosion resistance and machinability comparable to austenitic 304 stainless. Being martensitic, 17-4 is magnetic.

### APPLICABLE SPECIFICATIONS

ASTM A564/A564M Type 630, ASME SA564/SA564M

NACE MR-0175/ISO 15156

### HEAT TREATMENT – SOLUTION ANNEALED & AGED

CONDITION	Age Temperature °C (°F)	Time, h	Quench
H1150D	620 (1150)	4	Air Cool plus.....
	620 (1150)	4	Air Cool

### CHEMICAL ANALYSIS RANGE

ELEMENT	WEIGHT %	ELEMENT	WEIGHT %
C	0.07 Max	Cr	15.00 to 17.50
Si	1.00 Max	Cu	3.00 to 5.00
Mn	1.00 Max	Ni	3.00 to 5.00
S	0.03 Max	P	0.04 Max

### TYPICAL MECHANICAL PROPERTIES ≤8" (203.2mm)

**(Min Unless Stated)**

Condition	0.2% Yield ksi (MPa)	UTS ksi (MPa)	Ductility		Full size (10mm x 10mm) Charpy V Notch @ -46°C Ft-lbs (J)	Hardness HBW (HRC)
			%El 4D	%RA		
H1150	105 (725)	125 (860)	16	50	15 (20)	255-311 (24-33)

The data contained in this datasheet is for informational purposes only.  
Information may be revised at any time without prior notice.

Intoco Special Steels makes no representation or warranty of any kind (express or implied) and assumes no liability with respect to the accuracy or completeness of the information contained herein.

Although the data is believed to be representative of the product, the actual characteristics or performance of the product may vary from what is shown in this publication.

Nothing contained in this publication should be construed as guaranteeing the product for a particular use or applications

CONTACT DETAILS

Email: [sales@intoco.co.uk](mailto:sales@intoco.co.uk)

Telephone: 01452 712519